

PRODUCT DATA SHEET

Sikaplan® G-15

POLYMERIC MEMBRANE FOR MECHANICALLY FASTENED ROOF WATERPROOFING



DESCRIPTION

Sikaplan® G-15 (thickness 1.5mm) is a polyester reinforced multilayer, synthetic roof waterproofing sheet based on premium-quality polyvinyl chloride (PVC) according to EN 13956.

USES

Waterproofing membrane for exposed flat roofs:

- Mechanically fastened roofing systems.

CHARACTERISTICS / ADVANTAGES

- Resistant to permanent UV irradiation.
- Resistant to permanent wind exposure.
- High water vapour permeability.
- Resistant to all common environmental influences.
- Hot air welding without use of open flames.
- Recyclable.

SUSTAINABILITY

- Conformity with LEED v4 SSc 5 (Option 1): Heat Island Reduction - Roof (only traffic white).
- Conformity with LEED v4 MRc 2 (Option 1): Building Product Disclosure and Optimization – Environmental Product Declarations.
- Conformity with LEED v4 MRc 3 (Option 2): Building Product Disclosure and Optimization - Sourcing of Raw Materials.
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients.
- Conformity with LEED v2009 SSc 7.2 (Option 1): Heat Island Effect - Roof (only traffic white).
- Conformity with LEED v2009 MRc 4 (Option 2): Recycled Content.
- Environmental Product Declaration (EPD) available.

APPROVALS / CERTIFICATES

- Polymeric sheets for roof waterproofing according to EN 13956, certified by notified body 1213-CPD-4125/4127 and provided with the CE-mark.
- Reaction to fire according to EN 13501-1. Class E.
- External fire performance tested according to ENV 1187 and classified according to EN 13501-5: BROOF(t1), BROOF(t3).
- Factory Mutual (FM) Approval Class: 4470.
- Quality Management system in accordance with EN ISO 9001/14001.

PRODUCT INFORMATION

Packaging	Roll length:	20.00 m	20.00 m	20.00 m	20.00 m
	Roll width:	0.77 m	1.00 m	1.54 m	2.00 m
	Roll weight:	27.72 kg	36.00 kg	55.44 kg	72.00 kg
Appearance / Colour	Surface:	structured			
	Colours:				
	Top surface:	light grey (nearest RAL 7047) slate grey (nearest RAL 7015) brick red (nearest RAL 8004) pale green (nearest RAL 6021) traffic white (nearest RAL 9016)			
	Bottom surface:	dark grey			
	Top surface of sheet in other colours available on request, subject to minimum order quantities.				
Shelf life	5 years from date of production in unopened, undamaged and original packaging.				
Storage conditions	Rolls must be stored between +5 °C and +30 °C in a horizontal position on pallet, protected from direct sunlight, rain and snow. Do not stack pallets of rolls or any other material during transport or storage.				
Product Declaration	EN 13956				
Visible Defects	Pass				(EN 1850-2)
Length	20 m (- 0 % / + 5 %)				(EN 1848-2)
Width	0.77 m / 1.00 m / 1.54 m / 2.00 m (- 0.5 % / + 1 %)				(EN 1848-2)
Effective Thickness	1.5 mm (- 5 % / + 10 %)				(EN 1849-2)
Straightness	≤ 30 mm				(EN 1848-2)
Flatness	≤ 10 mm				(EN 1848-2)
Mass per unit area	1.8 kg/m ² (- 5 % / + 10 %)				(EN 1849-2)

TECHNICAL INFORMATION

Resistance to Impact	hard substrate	≥ 400 mm	(EN 12691)
	soft substrate	≥ 700 mm	
Hail Resistance	rigid substrate:	≥ 18 m/s	(EN 13583)
	flexible substrate:	≥ 30 m/s	
Tensile Strength	longitudinal (md) ¹⁾	≥ 1000 N/50 mm	(EN 12311-2)
	transversal (cmd) ²⁾	≥ 900 N/50 mm	
1) md = machine direction 2) cmd = cross machine direction			
Elongation	longitudinal (md) ¹⁾	≥ 15 %	(EN 12311-2)
	transversal (cmd) ²⁾	≥ 15 %	
1) md = machine direction 2) cmd = cross machine direction			
Dimensional Stability	longitudinal (md) ¹⁾	≤ 0.5 %	(EN 1107-2)
	transversal (cmd) ²⁾	≤ 0.5 %	
1) md = machine direction 2) cmd = cross machine direction			
Tear Strength	longitudinal (md) ¹⁾	≥ 150 N	(EN 12310-2)
	transversal (cmd) ²⁾	≥ 150 N	
1) md = machine direction 2) cmd = cross machine direction			

Joint Peel Resistance	no failure of the joint			(EN 12316-2)	
Joint Shear Resistance	≥ 600 N/50 mm			(EN 12317-2)	
Foldability at Low Temperature	≤ -25 °C			(EN 495-5)	
External Fire Performance	BROOF(t1) < 20° BROOF(t3) < 10°			(EN 13501-5)	
Reaction to Fire	Class E		(EN ISO 11925-2, classification to EN 13501-1)		
Effect of Liquid Chemicals, Including Water	On request			(EN 1847)	
Resistance to UV Exposure	Pass (> 5000 h / grade 0)			(EN 1297)	
Water Vapour Transmission	μ = 20 000			(EN 1931)	
Watertightness	Pass			(EN 1928)	
Solar Reflectance Index	Colour	Initial	3 years aged	Test institute (ASTM E 1980)	
	RAL 9016	109	81		CRRC
	RAL 7047	61			Sika
CRRC tested products are listed in Cool Roof Rating Council (CRRC) product data base.					
USGBC LEED Rating	Colour	Initial	3 years aged	(ASTM E 1980)	
	RAL 9016	SRI > 82	-		
Conform on the minimum requirements of LEED V4 SS credit 5 option 1 Heat Island reduction - Roof.					

SYSTEMS

System Structure

The following accessories shall be used:

- Sikaplan® D-18 or Sikaplan® S-15 un-reinforced sheet for detailing.
- Moulded corner pieces, prefabricated corners and pipe flashings
- Sika-Trocal® Metal Sheet Type S
- Sika-Trocal® Cleaner 2000
- Sika-Trocal® Cleaner L 100
- Sika-Trocal® Welding Agent
- Sika-Trocal® Seam Sealant
- Sika-Trocal® C 733 (contact adhesive)

Compatibility

Not compatible with direct contact to other plastics, e.g. EPS, XPS, PUR, PIR or PF. Not resistant to tar, bitumen, oil and solvent containing materials.

APPLICATION INFORMATION

Ambient Air Temperature -15 °C min. / +60 °C max.

Substrate Temperature -25 °C min. / +60 °C max.

APPLICATION INSTRUCTIONS

product properties.

SUBSTRATE QUALITY

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc. Sikaplan® G-15 must be separated from any incompatible substrates by an effective separation layer to prevent accelerated ageing. Prevent from direct contact with bitumen, tar, fat, oil, solvent containing materials and direct contact to other plastic materials, e.g. expanded polystyrene (EPS), extruded polystyrene (XPS), polyurethane (PUR), polyisocyanurate (PIR) or phenolic foam (PF) as this could adversely affect the

APPLICATION

Installation works must be carried out only by Sika instructed contractors for roofing.
Installation of some ancillary products, e.g. contact adhesives / thinners is limited to temperatures above +5 °C. Please refer to the respective Product Data Sheets. Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

APPLICATION METHOD / TOOLS

Installation procedure:

According to the valid installation instructions for Sikaplan®-G -type system for mechanically fastened roofing systems.

Fixing Method:

The roof waterproofing sheet is installed by loose laying with mechanical fastening in seam overlaps or independent from overlaps.

Welding Method:

Overlap seams are welded by electric hot welding equipment, such as manual hot air welding machines and pressure rollers or automatic hot air welding machines with controlled hot air temperature capability of minimum 600 °C.

Recommended type of equipment:

LEISTER TRIAC for manual welding
LEISTER VARIMAT for automatic welding
Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic situation prior to welding. The effective width of welded overlaps must be minimum 20 mm.
The seams must be mechanically tested with screw driver to ensure the integrity / completion of the weld. Any imperfections must be rectified by hot air welding. Cold welding of sheet overlaps with Sika-Trocal® Welding Agent is permitted for small repair work within application limits. Cold welded seam edges must be sealed with Sika-Trocal® Seam Sealant after testing.

LIMITATIONS

Geographical / Climate

The use of Sikaplan® G-15 membranes is limited to geographical locations with average monthly minimum temperatures of -25 °C.
Permanent ambient temperature during use is limited to +50 °C.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

Fresh air ventilation must be ensured, when working (welding) in closed rooms.

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1% (w/w).

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Hellas ABEE
15 Protomagias Str.
14568 Kryoneri
Attica-Greece
Tel.: +30 210 8160 600
Fax: +30 210 8160 606
www.sika.gr | sika@gr.sika.com



SikaplanG-15_en_GR_(09-2017)_1_1.pdf

Product Data Sheet
Sikaplan® G-15
September 2017, Version 01.01
020905011000151001