

PRODUCT DATA SHEET

Sika® WT-200 P

WATER RESISTING AND CRYSTALLINE WATERPROOFING CONCRETE ADMIXTURE



DESCRIPTION

Sika® WT-200 P is a combined water resisting and crystalline waterproofing admixture used to reduce the permeability of concrete and to enhance the self-healing abilities of the concrete.

USES

Sika® WT-200 P has been specifically formulated to produce high quality waterproof concrete. Sika® WT-200 P treated concrete is used as a part of the Sika® Watertight Concrete System.

Sika® WT-200 P can be used in any below / in / above ground watertight structures such as:

- Basements
- Parking garages
- Utility / plant rooms
- Tunnels
- Swimming pools
- Water retaining structures
- Dams
- Waste water treatment structures
- Underground commercial facilities (malls, transportation hubs etc.)

CHARACTERISTICS / ADVANTAGES

Sika® WT-200 P consists of a mixture of cements, amino alcohols and fillers. These active materials will form non-soluble materials throughout the pore and capillary structure of the concrete and seal the concrete permanently against penetration of water and other liquids. In addition the special formula and ingredients of Sika® WT-200 P enhances the self-healing properties of concrete and will improve the ability to heal cracks in concrete.

Sika® WT-200 P has the following characteristics and benefits:

- Reduced water penetration under pressure
- Reduced water absorption
- Enhancement of self-healing properties of the concrete
- Improvement in resistance against chemical attack
- Reduced vapour transmission

APPROVALS / CERTIFICATES

CE-marking and Declaration of Performance as Water resisting admixture & Water reducing/plasticizing admixture (Tables 9 & 2) according to EN 934.02:2009+A1:2012, based on certificate of factory production control issued by notified factory production control certification body and type testing.

PRODUCT INFORMATION

Composition	Mixture of cements, amino alcohols and fillers
Packaging	18 kg bags 1,75 kg water soluble bags (10x1,75 kg)
Appearance / Colour	Greyish powder
Shelf life	12 months from date of production if stored in unopened and undamaged original sealed containers.
Storage conditions	Storage properly in original, sealed, undamaged packaging at temperatures between +5°C and +35°C. Protect from direct sunlight, moisture, frost

and contamination.

Bulk Density ~750 kg/m³

Equivalent Sodium Oxide ≤ 3%

TECHNICAL INFORMATION

Concreting Guidance	<p>The standard rules of good concreting practice, concerning production and placing, are to be followed. Laboratory trials shall be carried out before concreting on site, especially when using a new mix design or producing new concrete components. Fresh concrete must be cured properly and curing applied as early as possible.</p>
Concrete Mix Design	<ul style="list-style-type: none">▪ For waterproof concrete: Concrete mix design depends on local requirements and / or local standards for watertight concrete systems.▪ For Sika® Watertight Concrete: Sika® WT-200 P has been formulated for use in concrete with a minimum binder content of 350 kg/m³ and a maximum w/b-ratio of 0.45. Depending on the specific mix design the dosage of HRWR/superplasticizer has to be evaluated in order to achieve a S3 / F4 consistence class (EN 206-1).▪ Laboratory trials are always recommended to evaluate and confirm actual water reduction and consistence class.
Effect on Setting	<p>The chemical and physical composition of the components, concrete, Sika® WT-200 P and concrete and ambient temperature can affect the setting time of the concrete.</p>

APPLICATION INFORMATION

Recommended Dosage	1–2 % of Sika® WT-200 P by weight of binder
Compatibility	<p>Sika® WT-200 P may be combined with many other Sika products. Note: Always conduct trials before combining products in specific mixes and contact Sika technical service for more information and advice.</p>
Dispensing	<ul style="list-style-type: none">▪ Sika® WT-200 P is added at the time of batching to the concrete.▪ Depending on the operation it is either added to the gauging / mixing water to form a very thin slurry and add it into the concrete mixer.▪ Or add Sika® WT-200 P to the fine and coarse aggregate. The aggregates and Sika® WT-200 P have to be mixed thoroughly for about 120 seconds before adding cement and gauging / mixing water.▪ A wet mixing time, which is depending on the mixing conditions and mixer performance, of at least 60 seconds is recommended.▪ To avoid excess water in the concrete, the final dosage must begin only after 2/3 of the wet mixing time.▪ The water/binder-ratio and consistency control, remains as responsibility of the concrete producer. Laboratory trials are recommended to evaluate and confirm the actual flowability and workability.
Restrictions	<p>When using of Sika® WT-200 P in combination with SCM, the SCM content should be limited to max. 40 % of total binder content (Fly ash / GGBFS / Silica fume).</p>

IMPORTANT CONSIDERATIONS

When using Sika® WT-200 P a suitable mix design has to be taken into account and local material sources shall be tested.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Hellas ABEE

15 Protomagias Str.
14568 Kryoneri
Attica-Greece
Tel.: +30 210 8160 600
Fax: +30 210 8160 606
www.sika.gr | sika@gr.sika.com



Product Data Sheet

Sika® WT-200 P
December 2019, Version 01.04
021403011000000094

SikaWT-200P-en-GR-(12-2019)-1-4.pdf